

Endecotts' Finest: Woven Wire Mesh Sieves

Endecotts woven wire mesh sieves are the most widely used test sieves for all types of laboratory sampling and particle size analysis. They are made with only the highest quality materials and are available in diameter sizes of 100, 200, 300, 400 and 450 mm or in 3, 8, 12 or 18 inches.

They can be supplied with aperture sizes ranging from 125 mm down to 20 microns in full or half height versions. Woven wire mesh sieves are available in frame materials of either stainless steel or brass (400 and 450 mm only available in stainless steel).

Advantages

- Precision frame (ensures consistent nestability)
- Precise aperture (in accordance with ISO 3310, ASTM E11 or other specifications)
- Made to International Standards
- Natural fillet (free flowing of sample)
- Totally sealed (no crevice to lose material)
- Evenly tensioned mesh ensures accurate analysis
- Safe edge (big radius makes it comfortable to handle)
- Serial number (ensures full traceability)

**HIGH STANDARD
IN SIEVE ANALYSIS**



Endecotts Standard Woven Wire Mesh Sieves are available in these sizes

International Test Sieve Series

ISO 3310-1

Nominal Aperture Sizes



125.00 mm	26.50 mm	5.60 mm	1.18 mm	250 µm	53 µm
112.00 mm	25.00 mm	5.00 mm	1.12 mm	224 µm	50 µm
106.00 mm	22.40 mm	4.75 mm	1.00 mm	212 µm	45 µm
100.00 mm	20.00 mm	4.50 mm	900 µm	200 µm	40 µm
90.00 mm	19.00 mm	4.00 mm	850 µm	180 µm	38 µm
80.00 mm	18.00 mm	3.55 mm	800 µm	160 µm	36 µm
75.00 mm	16.00 mm	3.35 mm	710 µm	150 µm	32 µm
71.00 mm	14.00 mm	3.15 mm	630 µm	140 µm	25 µm
63.00 mm	13.20 mm	2.80 mm	600 µm	125 µm	20 µm
56.00 mm	12.50 mm	2.50 mm	560 µm	112 µm	
53.00 mm	11.20 mm	2.36 mm	500 µm	106 µm	
50.00 mm	10.00 mm	2.24 mm	450 µm	100 µm	
45.00 mm	9.50 mm	2.00 mm	425 µm	90 µm	
40.00 mm	9.00 mm	1.80 mm	400 µm	80 µm	
37.50 mm	8.00 mm	1.70 mm	355 µm	75 µm	
35.50 mm	7.10 mm	1.60 mm	315 µm	71 µm	
31.50 mm	6.70 mm	1.40 mm	300 µm	63 µm	
28.00 mm	6.30 mm	1.25 mm	280 µm	56 µm	

American Standard Sieve Series

ASTM E11

Sieve Designation



Standard	Altern.	Standard	Altern.	Standard	Altern.
125.00 mm	5.00	9.50 mm	3/8	425 µm	No.40
106.00 mm	4.24	8.00 mm	5/16	355 µm	No.45
100.00 mm	4	6.70 mm	0.265	300 µm	No.50
90.00 mm	3 1/2	6.30 mm	1/4	250 µm	No.60
75.00 mm	3	5.60 mm	No. 3 1/2	212 µm	No.70
63.00 mm	2 1/2	4.75 mm	No. 4	180 µm	No.80
53.00 mm	2.12	4.00 mm	No. 5	150 µm	No.100
50.00 mm	2	3.35 mm	No. 6	125 µm	No.120
45.00 mm	1 3/4	2.80 mm	No. 7	106 µm	No.140
37.50 mm	1 1/2	2.36 mm	No. 8	90 µm	No.170
31.50 mm	1 1/4	2.00 mm	No.10	75 µm	No.200
26.50 mm	1.06	1.70 mm	No.12	63 µm	No.230
25.00 mm	1	1.40 mm	No.14	53 µm	No.270
22.40 mm	7/8	1.18 mm	No.16	45 µm	No.325
19.00 mm	3/4	1.00 mm	No.18	38 µm	No.400
16.00 mm	5/8	850 µm	No.20	32 µm	No. 450
13.20 mm	0.530	710 µm	No.25	25 µm	No. 500
12.50 mm	1/2	600 µm	No.30	20 µm	No. 635
11.20 mm	7/16	500 µm	No.35		